



Optimization of Calcium Alginate Hydrogel Bioencapsulation of *Acinetobacter junii* B6, a Lipopeptide Biosurfactant Producer

Borhanabadi, M. A., Estabragh, M. A. R., Dehghannoudeh, G., Banat, I. M., Ohadi, M., & Moshafi, M. H. (2023). Optimization of Calcium Alginate Hydrogel Bioencapsulation of *Acinetobacter junii* B6, a Lipopeptide Biosurfactant Producer. *Jundishapur Journal of Natural Pharmaceutical Products*, 18(2), 1-8. Article 134325. Advance online publication. <https://doi.org/10.5812/jjnpp-134325>

[Link to publication record in Ulster University Research Portal](#)

Published in:

Jundishapur Journal of Natural Pharmaceutical Products

Publication Status:

Published online: 13/05/2023

DOI:

[10.5812/jjnpp-134325](https://doi.org/10.5812/jjnpp-134325)

Document Version

Publisher's PDF, also known as Version of record

Document Licence:

CC BY-NC

General rights

The copyright and moral rights to the output are retained by the output author(s), unless otherwise stated by the document licence.

Unless otherwise stated, users are permitted to download a copy of the output for personal study or non-commercial research and are permitted to freely distribute the URL of the output. They are not permitted to alter, reproduce, distribute or make any commercial use of the output without obtaining the permission of the author(s).

If the document is licenced under Creative Commons, the rights of users of the documents can be found at <https://creativecommons.org/share-your-work/licenses/>.

Take down policy

The Research Portal is Ulster University's institutional repository that provides access to Ulster's research outputs. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact pure-support@ulster.ac.uk



Optimization of Calcium Alginate Hydrogel Bioencapsulation of *Acinetobacter junii* B6, a Lipopeptide Biosurfactant Producer

Mohammadhossein Ahmadi Borhanabadi ^{#1,2}, Mohammad Amin Raeisi Estabragh ^{ib #3}, Gholamreza Dehghannoudeh ⁴, Ibrahim M Banat ⁵, Mandana Ohadi ^{4,*} and Mohammad Hassan Moshafi ^{4,**}

¹Department of Traditional Pharmacy, Faculty of Persian Medicine, Kerman University of Medical Sciences, Kerman, Iran

²Student Research Committee, Kerman University of Medical Sciences, Kerman, Iran

³Department of Pharmaceutics, Faculty of Pharmacy, Kerman University of Medical Sciences, Kerman, Iran

⁴Pharmaceutics Research Center, Institute of Neuropharmacology, Kerman University of Medical Sciences, Kerman, Iran

⁵Pharmaceutical Research Group, School of Biomedical Sciences, Ulster University, Coleraine, Northern Ireland, UK

* Corresponding author: Pharmaceutics Research Center, Institute of Neuropharmacology, Kerman University of Medical Sciences, Kerman, Iran. Email: mandanaohady@gmail.com

** Corresponding author: Pharmaceutics Research Center, Institute of Neuropharmacology, Kerman University of Medical Sciences, Kerman, Iran. Email: moshafi14@yahoo.com

These authors are contributed equally as the first author.

Received 2022 December 21; Revised 2023 April 04; Accepted 2023 April 09.

Abstract

Background: Biosurfactants are derived from microbes, plants, and animals. *Acinetobacter junii* B6 is a lipopeptide biosurfactant producer previously investigated for its structure, physicochemical, and product aggregation properties.

Objectives: In this study, we investigated and optimized the bioencapsulation of *A. junii* B6 in calcium alginate hydrogel.

Methods: *A. junii* B6 was encapsulated using calcium alginate hydrogel. The formulation of the hydrogel was optimized using a full factorial approach. Sodium alginate concentration, calcium chloride concentration, and hardening time were selected as the main factors, and surface tension was the response measure. A scanning electron microscope (SEM) was used to study the bead's morphology.

Results: Scanning electron microscope image showed rounded and smooth beads. The most biosurfactant production and reduced surface tension (35.98 mN/m) were observed at concentrations of 1% calcium chloride, (1%) sodium alginate, and 15 minutes of hardening time. *A. junii* B6 can be encapsulated in alginate hydrogels producing biosurfactant at optimum experimental design.

Conclusions: This represents a practical method for optimizing the bioencapsulation of *A. junii* B6 to produce biosurfactants.

Keywords: *Acinetobacter junii* B6, Bioencapsulation, Biosurfactant, Calcium Alginate, Optimization

1. Background

Surfactants' structure consists of both hydrophilic and hydrophobic moieties that play an important role in drug delivery and many industries, including oil and petroleum, soap and detergent, energy generation, food and beverage, and environmental pollution remediation (1-5). Biosurfactants are new-age surfactants derived from plants, animals, and microbes (6, 7). They are equally diverse in structure and function and are gaining attention due to their biodegradability, stability in high salinity, acidity, and temperature, and they have lower critical micelle concentration (CMC) values than synthetic surfactants (6, 8, 9). Biosurfactants are divided into four main types: Glycolipids, lipopeptides, phospholipids, and polymers. Glycolipids and glycoproteins are produced by different strains of bacteria (8). The type of lipopeptide

presents a heterogeneous class of biologically active peptides. Lipopeptides contain hydrocarbon chains or fatty acids that are hydrophobic and hydrophilic peptide chains typically produced by various bacteria, such as members of the *Acinetobacter* genus (10-12). The *Acinetobacter* genus has received more attention because it is widely used in the petroleum industry (13). *Acinetobacter junii* B6 was isolated from an Iran oil drilling site (11, 14). Investigations of *A. junii* B6 lipopeptide biosurfactant's structure, physicochemical, and aggregation properties have been carried out, and the CMC was evaluated at about 300 mg/L (11).

Despite the numerous benefits of biosurfactants to many industries, the greatest limit to using them in many manufacturing processes is their high production cost. One of the efficient techniques to produce biosurfactants is through bioencapsulation (15, 16). The bioencapsulation

of growing bacterial cells is attractive because it provides bio-transformational and biosynthetic abilities to produce diverse valuable products such as biosurfactants, antibiotics, enzymes, and organic acids (15, 17-20). Several advantages are provided by bioencapsulation for the production of biosurfactants, including the ability to separate cell mass from bulk liquid for reuse, ensuring continuous operation over an extended period, and increasing reactor productivity (15, 17, 19). Various natural and synthetic polymers have been used in bioencapsulation and drug delivery (21). The mild gelling, biocompatibility, and biodegradability of alginate make it popular in the food and pharmaceutical industries. Alginate has also been used to microencapsulate therapeutic agents for prolonged and controlled drug delivery (19, 22, 23). In addition to being simple, nontoxic, and inexpensive, entrapment in calcium alginate is also one of the most suitable methods for bioencapsulation (18). Hydrogels are a three-dimensional and crosslinked network of hydrophilic polymers. They can absorb a large amount of water or biological fluids, which leads to their swelling while maintaining their 3D structure without dissolving since calcium alginate hydrogels can be used instead of calcium alginate beads. Applying the statistical design of experiments to the immobilization method improves product yields, further validating the response to the desired product, which saves time and overall cost. Three steps of the design expert (randomization, replication, and blocking) are used to improve the efficiency of experimentation (24-26).

2. Objectives

The main aim of this study was to optimize the bioencapsulation of biosurfactant-producing *A. junii* B6 in calcium alginate hydrogel using the two-level factorial method and observing the effect of bioencapsulation in increasing microorganism's resistance to harsh conditions and biosurfactant production. Sodium alginate concentration, calcium chloride concentration, and hardening time were selected as factors, and surface tension was the main test design response. Since the amount of biosurfactant production indicates the number of encapsulated microorganism cells, the amount of biosurfactant production was used as an index for optimization (15).

3. Methods

3.1. Primary Culture of *Acinetobacter junii* B6

A. junii B6 was isolated from an Iranian oil excavation site and characterized in our previous study (14). Primary

cultures were prepared by transferring from prolonged-storage vials to a solid mineral salt medium containing one percent crude oil as the only carbon source and incubated at 37°C overnight (11).

3.2. Preparation of Bioencapsulation Beads of *A. junii* B6

Sodium alginate solution and calcium chloride were prepared under sterile conditions and at different concentrations. A 1% (v/v) of a microbial suspension ($OD_{600} = 0.8$) was gently mixed with sodium alginate solution for one hour to obtain a homogeneous mixture. The resulting mixture was removed by a 10 mL sterile syringe with a 23 G stainless steel needle and sprayed dropwise at a distance of 5 cm into a stirred calcium chloride solution.

3.3. Surface Tension Measurements

The measurement of surface tension (at room temperature) was done by plate method according to Wilhelmy using a tensiometer (krüss® tensiometer k100) compared to the negative control (culture medium without bacteria). The device's surface tension reading accuracy was measured with absolute ethanol and distilled water before each reading (14). The beads, after preparation, are separated and washed and then added to the culture medium. The measurement of the surface tension of the supernatant culture medium (1500 rpm, 5 min) after equilibrium was investigated as a measure of biosurfactant production and the main response of the experimental design (15).

3.4. Optimization of Bioencapsulation

An experimental design of two factorial methods was used to identify the most important factors potentially affecting the bioencapsulation of *A. junii* B6 and the production of biosurfactants. The selected factors were sodium alginate concentration, calcium chloride concentration, and hardening time. The specified codes for each factor and its levels are presented in Table 1. According to the design of the experiment using the two-factor factorial method, 8 (23) experimental setups were designed and carried out using Design Expert 7.0.0 software. In subsequent steps, the two-factor interaction (2FI) model following the equation below was used to estimate the mathematical relationship between variables.

$$y = \beta_0 + \sum_{i=1}^3 \beta_i X_i + \sum_{i=1}^3 \beta_{ij} \quad (1)$$

The predicted response is y, the coded levels of the independent variables are represented as X, β_0 is the model constant, β_i is the linear coefficient, and β_{ij} is the cross-product coefficient.

Table 1. Factors and Levels Used in the Design of a Two-level Factorial to Produce the Maximum Amount of Biosurfactant

Factor	Symbol	Unit	Level		
			Low	Center	High
Alginate concentration	A	(%w/v)	1	2	3
CaCl ₂ concentration	B	(%w/v)	1	2.5	4
Hardening time	C	(min)	15	20	25

Moreover, to ensure the accuracy of the results, the center point was repeated three times, and the results were compared. Analysis of variance (ANOVA) was carried out on the obtained results.

3.5. Scanning Electron Microscope Analysis

An scanning electron microscope (SEM) was used to examine the shape of the beads. Calcium alginate beads were prepared at different concentrations, transferred to a liquid Mineral salt medium containing 1% oil, and incubated at 37°C and 150 rpm for 48 h. In a fume hood at room temperature, beads were dehydrated using an increasingly graded ethanol series (10, 50, 70, 90, and 100%). After this period, the shape and stability of the beads were assessed using field emission scanning electron microscopy (FE-SEM, MIRA 3 XM, Tescan Inc., USA). A gold sputter coating was carried out for five minutes after the samples were dried at room temperature and mounted on aluminum stubs. An acceleration voltage of 15 kV was applied to samples (14, 27, 28).

4. Results

The direct method was used for the bioencapsulation of bacteria. Calcium alginate beads were formed and encapsulated *A. junii* B6 as a lipopeptide biosurfactant producer. In the study of Chan and Zhang this method was used for the bioencapsulation of *Lactobacillus acidophilus* in alginate, and bioencapsulation protected bacteria from harsh conditions (29).

4.1. Optimization of Bioencapsulation

To determine the effects of the independent variables, the experimental design was performed according to Table 2. The concentration of calcium chloride and sodium alginate and the hardening time of beads greatly affected the production of biosurfactants by *A. junii* B6. The surface tension as the response was calculated using the following equation:

$$\text{Surface tension} = 40.64 + 1.66 (B) + 1.99 (C) - 1.31 (A \times B) - 1.89 (A \times C) + 2.56 (B \times C) + 0.59 (A \times B \times C)$$

A, B, and C are the concentration of sodium alginate and calcium chloride and the hardening time of beads, respectively.

The results of the measurement of surface tension in different conditions were examined by experimental design software to develop the best conditions that can describe the observed response. The validity of the proposed model was measured by the ANOVA test, the results of which are presented in Table 3.

A, B, and C show the main effects of the independent variables, including sodium alginate, calcium chloride concentration, and hardening time, respectively. The variables AB, AC, and BC indicate the intervening effect of sodium alginate (factor A) and calcium chloride (factor B) and hardening time (factor C).

The results show that the P-value for the proposed model is less than 0.05, and therefore the proposed model was significant (P-value \leq 0.0249). Also, the curvature (P-value \geq 0.3525) and the lack of fit (P-value \geq 0.7031) were non-significant. Another test used to validate the models was the linear regression test. The regression coefficients ($R^2 = 0.96$, adjusted regression coefficient = 0.9) and predictive regression coefficient (0.75) were calculated and reported in this test. According to the results, the model has a high precision of 39.38, and the reliability of the experimental values was remarkable (coefficient of variation = 3.34%).

Calcium chloride concentration and hardening time as independent variables were significant (P-value \leq 0.0368, P-value \leq 0.0231, respectively). The intervening effect of sodium alginate (factor A) and calcium chloride (factor B), sodium alginate (factor A) and hardening time (factor C), and calcium chloride (factor B) and hardening time (factor C) were also significant (Table 3). Based on regression, the intervening effect of sodium alginate and hardening time (AC) has the most positive effect (coefficient = -1.89) on optimal bioencapsulation (lower surface tension). Figure 1 shows the fit of the surface tension (mN/m) values observed during the experiment (actual) and the surface tension values predicted by the software model presented.

Figure 2A shows the simultaneous effect of two variables, calcium chloride and hardening time. Figure 2B

Table 2. Experimental Design and Results of Two Factorial Levels

Run	Value of Independent Factor			Surface Tension (mN/m)
	A	B	C	Experimental
1	-1	1	1	49.72 ± 0.04
2	1	-1	-1	43.11 ± 0.03
3	-1	-1	-1	35.98 ± 0.03
4	1	1	1	44.08 ± 0.05
5	-1	-1	1	39.81 ± 0.04
6	-1	1	-1	38.09 ± 0.03
7	1	1	-1	37.55 ± 0.06
8	1	-1	1	37.07 ± 0.09
9	0	0	0	38.09 ± 0.02
10	0	0	0	40.08 ± 0.08
11	0	0	0	41.04 ± 0.08

Table 3. Result of Analysis of Variance Test for the Experimental Model

Source	Sum of Squares	Degree of Freedom	Mean Square	F-Value	P-Value Prob > F
Model	151.29	6	25.21	14.78	0.0249
B	22.11	1	22.11	12.96	0.0368
C	31.60	1	23.60	18.52	0.0231
AB	13.78	1	13.78	8.08	0.0655
AC	28.50	1	28.50	16.71	0.0265
BC	52.53	1	52.53	30.79	0.0115
ABC	2.76	1	2.76	1.62	0.2929
Curvature	2.06	1	2.06	1.21	0.3525
Residual	5.12	3	1.71	-	-
Lack of fit	0.45	1	0.45	0.19	0.7031
Pure error	4.67	2	2.33	-	-

shows the simultaneous effect of two variables, the concentration of calcium chloride and sodium alginate, on the production of biosurfactants and the reduction of surface tension by *A. junii* B6.

Figure 2C show the simultaneous effect of two variables, sodium alginate and hardening time, on the surface tension.

4.2. Morphology and Stability of Beads

Scanning electron microscope was used to examine the morphological characteristics of the beads, and the imaging results are shown in Figure 3. The beads were round, had a smooth surface, and had no obvious dents. The shape and stability of the beads were assessed and run 3 (lowest level of calcium chloride (1%), sodium alginate (1%), and the hardening time of 15 minutes), resulting in more stable and spherical-shaped beads.

5. Discussion

The results showed that the amount of calcium chloride and sodium alginate at the lowest level (1%) and the hardening time at its lowest level (15 minutes) had the greatest effect on the production of biosurfactants and reduced surface tension to 35.98 mN/m by *A. junii* B6. In the study by Wu et al. for bioencapsulation of *Klebsiella oxytoca* sodium alginate and calcium chloride were optimally used and 1.5 - 2.0% and 2.0% concentrations, respectively (30). The result of this study is in contrast with our previous study that *Pseudomonas aeruginosa* encapsulated in alginate beads which may be because the higher concentration of sodium alginate solution became highly viscous. It isn't easy to pump, so crosslinking and bead forming are hampered and unstable (31, 32). At a high concentration of calcium chloride, bioencapsulation efficacy is decreased.




Figure 1. Graph of the observed surface tension (mN/m) values against the values predicted by the software model




Figure 2. A, three-dimensional graph of the simultaneous effect of calcium chloride and hardening time on the surface tension; B, three-dimensional diagram of the simultaneous effect of sodium alginate and calcium chloride on the surface tension; C, three-dimensional diagram of the simultaneous effect of sodium alginate and hardening time on the surface tension




Figure 3. Scanning electron microscope (SEM) image of prepared beads containing calcium chloride and sodium alginate at (1%) with 15 minutes for the hardening bead (run 3)

This may be due to pore size reduction, resulting in diminished substrate penetration into the beads (16, 33). Also, increasing the concentration of calcium chloride, sodium alginate, and hardening time leads to harder beads, therefore decrease in the release rate of biosurfactant from inside the beads was observed. A higher coating thickness also decreased the release rate of encapsulated cells (29). Increasing the hardening time can also lead to increased cross-linking and reduced cavities, which may reduce the production of biosurfactants by reducing cell access to nutrients (34).

5.1. Conclusions

In this study, the production of a biosurfactant by alginate hydrogel encapsulated *A. junii* B6 was studied and optimized by experimental design. This experiment showed that a biosurfactant produced in bead formulation containing 1% solution of calcium chloride, 1% sodium alginate, and 15 minutes of hardening beads had a maximum surface tension reduction of 35.98 ± 0.03 mN/m. Finally, the practicality of this method and the possibility of creating a sequential culture system to produce biosurfactants

is of great importance for potential future production and commercialization.

Acknowledgments

The authors would like to thank the Kerman University of Medical Sciences (KMU) for facilitating research into this study.

Footnotes

Authors' Contribution: Mohammadhossein Ahmadi Borhanabadi and Mohammad Amin Raeisi Estabragh contributed equally as the first authors. Study concept and design: Mandana Ohadi and Mohammad Hassan Moshafi; Analysis and interpretation of data: Mohammadhossein Ahmadi Borhanabadi and Gholamreza Dehghannoudeh; Drafting of the manuscript: Mohammad Amin Raeisi Estabragh; Critical revision of the manuscript for important intellectual content: Mandana Ohadi, Ibrahim M Banat, and Gholamreza Dehghannoudeh; Statistical analysis: Mandana Ohadi, and Mohammad Amin Raeisi Estabragh.

Conflict of Interests: The authors declare no conflict of interest, financial or otherwise.

Data Reproducibility: The dataset presented in the study is available on request from the corresponding author during submission or after publication.

Funding/Support: There was no funding/support.

References

- Farias CBB, Almeida FCG, Silva IA, Souza TC, Meira HM, Soares da Silva RCF, et al. Production of green surfactants: Market prospects. *Electron J Biotechnol.* 2021;51:28–39. <https://doi.org/10.1016/j.ejbt.2021.02.002>.
- Sun W, Zhu B, Yang F, Dai M, Sehar S, Peng C, et al. Optimization of biosurfactant production from *Pseudomonas* sp. CQ2 and its application for remediation of heavy metal contaminated soil. *Chemosphere.* 2021;265:129090. [PubMed ID: 33293052]. <https://doi.org/10.1016/j.chemosphere.2020.129090>.
- Raeisi Estabragh MA, Sajadi Bami M, Ohadi M, Banat IM, Dehghanoudeh G. Carrier-Based Systems as Strategies for Oral Delivery of Therapeutic Peptides and Proteins: A Mini-Review. *Int J Pept Res Ther.* 2021;27(2):1589–96. <https://doi.org/10.1007/s10989-021-10193-0>.
- Ribeiro BG, Guerra JMC, Sarubbo LA. Potential Food Application of a Biosurfactant Produced by *Saccharomyces cerevisiae* URM 6670. *Front Bioeng Biotechnol.* 2020;8:434. [PubMed ID: 32457894]. [PubMed Central ID: PMC7221129]. <https://doi.org/10.3389/fbioe.2020.00434>.
- Raeisi Estabragh MA, Pardakhty A, Ahmadzadeh S, Dabiri S, Malekpour Afshar R, Farajli Abbasi M. Successful Application of Alpha Lipoic Acid Niosomal Formulation in Cerebral Ischemic Reperfusion Injury in Rat Model. *Adv Pharm Bull.* 2022;12(3):541–9. [PubMed ID: 35935040]. [PubMed Central ID: PMC9348526]. <https://doi.org/10.34172/apb.2022.058>.
- Marchant R, Banat IM. Biosurfactants: a sustainable replacement for chemical surfactants? *Biotechnol Lett.* 2012;34(9):1597–605. [PubMed ID: 22618240]. <https://doi.org/10.1007/s10529-012-0956-x>.
- Marchant R, Banat IM. Microbial biosurfactants: challenges and opportunities for future exploitation. *Trends Biotechnol.* 2012;30(11):558–65. [PubMed ID: 22901730]. <https://doi.org/10.1016/j.tibtech.2012.07.003>.
- Sajadi Bami M, Raeisi Estabragh MA, Ohadi M, Banat IM, Dehghanoudeh G. Biosurfactants aided bioremediation mechanisms: A mini-review. *Soil Sediment Contam Int J.* 2022;31(7):801–17. <https://doi.org/10.1080/15320383.2021.2016603>.
- Manga EB, Celik PA, Cabuk A, Banat IM. Biosurfactants: Opportunities for the development of a sustainable future. *Curr Opin Colloid Interface Sci.* 2021;56:101514. <https://doi.org/10.1016/j.cocis.2021.101514>.
- Ohadi M, Forootanfar H, Dehghanoudeh G, Eslaminejad T, Ameri A, Shakibaie M, et al. Antimicrobial, anti-biofilm, and anti-proliferative activities of lipopeptide biosurfactant produced by *Acinetobacter junii* B6. *Microb Pathog.* 2020;138:103806. [PubMed ID: 31629797]. <https://doi.org/10.1016/j.micpath.2019.103806>.
- Ohadi M, Dehghanoudeh G, Forootanfar H, Shakibaie M, Rajaei M. Investigation of the structural, physicochemical properties, and aggregation behavior of lipopeptide biosurfactant produced by *Acinetobacter junii* B6. *Int J Biol Macromol.* 2018;112:712–9. [PubMed ID: 29425877]. <https://doi.org/10.1016/j.ijbiomac.2018.01.209>.
- Zou C, Wang M, Xing Y, Lan G, Ge T, Yan X, et al. Characterization and optimization of biosurfactants produced by *Acinetobacter baylyi* ZJ2 isolated from crude oil-contaminated soil sample toward microbial enhanced oil recovery applications. *Biochem Eng J.* 2014;90:49–58. <https://doi.org/10.1016/j.bej.2014.05.007>.
- Jung J, Park W. *Acinetobacter* species as model microorganisms in environmental microbiology: current state and perspectives. *Appl Microbiol Biotechnol.* 2015;99(6):2533–48. [PubMed ID: 25693672]. <https://doi.org/10.1007/s00253-015-6439-y>.
- Ohadi M, Dehghanoudeh G, Shakibaie M, Banat IM, Pournamdari M, Forootanfar H. Isolation, characterization, and optimization of biosurfactant production by an oil-degrading *Acinetobacter junii* B6 isolated from an Iranian oil excavation site. *Biocatal Agric Biotechnol.* 2017;12:1–9. <https://doi.org/10.1016/j.cbab.2017.08.007>.
- Dehghanoudeh G, Kiani K, Moshafi MH, Dehghanoudeh N, Rajaei M, Salarpour S, et al. Optimizing the immobilization of biosurfactant-producing *Pseudomonas aeruginosa* in alginate beads. *J Pharm Pharmacogn Res.* 2019;7(6):413–20.
- Abang S, Chan ES, Poncelet D. Effects of process variables on the encapsulation of oil in ca-alginate capsules using an inverse gelation technique. *J Microencapsul.* 2012;29(5):417–28. [PubMed ID: 22292966]. <https://doi.org/10.3109/02652048.2012.655331>.
- Schoebitz M, López MD, Roldán A. Bioencapsulation of microbial inoculants for better soil-plant fertilization. A review. *Agron Sustain Dev.* 2013;33(4):751–65. <https://doi.org/10.1007/s13593-013-0142-0>.
- Mohapatra PK, Mondal KC, Pati BR. Production of tannase by the immobilized cells of *Bacillus licheniformis* KBR6 in Ca-alginate beads. *J Appl Microbiol.* 2007;102(6):1462–7. [PubMed ID: 17578410]. <https://doi.org/10.1111/j.1365-2672.2006.03207.x>.
- Amir Heidari B, Badinloo S, Ohadi M, Dehghanoudeh G. Bioencapsulation of Biosurfactant-Producing *Bacillus subtilis* (PTCC 1023) in Alginate Beads. *Jundishapur J Nat Pharm Prod.* 2016;11(4):e33935. <https://doi.org/10.17795/jjnpp-33935>.
- Loh JY, Lai KS, Lee PT, Liew HJ, Ting ASY. Effects of *Artemia nauplii* bioencapsulated with *Lactococcus lactis* subsp. *lactis* CF4MRS and sodium alginate on Edwardsiellosis protection and digestive enzyme production in climbing perch larvae, *Anabas testudineus* (Bloch, 1792). *J Appl Aquac.* 2021;35(1):51–68. <https://doi.org/10.1080/10454438.2021.1935389>.
- Khazaeli P, Alaei M, Khaksarihadad M, Ranjbar M. Preparation of PLA/chitosan nanoscaffolds containing cod liver oil and experimental diabetic wound healing in male rats study. *J Nanobiotechnology.* 2020;18(1):176. [PubMed ID: 33256764]. [PubMed Central ID: PMC7706058]. <https://doi.org/10.1186/s12951-020-00737-9>.
- Uyen NTT, Hamid ZAA, Tram NXT, Ahmad N. Fabrication of alginate microspheres for drug delivery: A review. *Int J Biol Macromol.* 2020;153:1035–46. [PubMed ID: 31794824]. <https://doi.org/10.1016/j.ijbiomac.2019.10.233>.
- Lori MS, Ohadi M, Estabragh MAR, Afsharipour S, Banat IM, Dehghanoudeh G. pH-Sensitive Polymer-Based Carriers as a Useful Approach for Oral Delivery of Therapeutic Protein: A Review. *Protein Pept Lett.* 2021;28(11):1230–7. [PubMed ID: 34303327]. <https://doi.org/10.2174/0929866528666210720142841>.
- Beg S, Swain S, Rahman M, Hasnain MS, Imam SS. Chapter 3 - Application of Design of Experiments (DoE) in Pharmaceutical Product and Process Optimization. In: Beg S, Hasnain MS, editors. *Pharmaceutical Quality by Design: Principles and Applications*. London: Academic Press; 2019. p. 43–64. <https://doi.org/10.1016/B978-0-12-815799-2.00003-4>.
- Ekpenyong M, Antai S, Asitok A, Ekpo B. Response surface modeling and optimization of major medium variables for glycolipopeptide production. *Biocatal Agric Biotechnol.* 2017;10:113–21. <https://doi.org/10.1016/j.cbab.2017.02.015>.
- Sharifi H, Zabihzadeh SM, Ghorbani M. The application of response surface methodology on the synthesis of conductive polyaniline/cellulosic fiber nanocomposites. *Carbohydr Polym.* 2018;194:384–94. [PubMed ID: 29801853]. <https://doi.org/10.1016/j.carbpol.2018.04.083>.
- Partovinia A, Vatankhah E. Experimental investigation into size and sphericity of alginate micro-beads produced by electrospraying technique: Operational condition optimization. *Carbohydr Polym.* 2019;209:389–99. [PubMed ID: 30732823]. <https://doi.org/10.1016/j.carbpol.2019.01.019>.

28. Ayarza J, Coello Y, Nakamatsu J. SEM-EDS study of ionically cross-linked alginate and alginic acid bead formation. *Int J Polym Anal Charact.* 2017;**22**(1):1-10. <https://doi.org/10.1080/1023666x.2016.1219834>.
29. Chan ES, Zhang Z. Bioencapsulation by compression coating of probiotic bacteria for their protection in an acidic medium. *Process Biochem.* 2005;**40**(10):3346-51. <https://doi.org/10.1016/j.procbio.2005.03.001>.
30. Wu Z, Zhao Y, Kaleem I, Li C. Preparation of calcium-alginate microcapsuled microbial fertilizer coating *Klebsiella oxytoca* Rs-5 and its performance under salinity stress. *Eur J Soil Biol.* 2011;**47**(2):152-9. <https://doi.org/10.1016/j.ejsobi.2010.11.008>.
31. Narsaiah K, Jha SN, Wilson RA, Mandge HM, Manikantan MR. Optimizing microencapsulation of nisin with sodium alginate and guar gum. *J Food Sci Technol.* 2014;**51**(12):4054-9. [PubMed ID: 25477680]. [PubMed Central ID: PMC4252430]. <https://doi.org/10.1007/s13197-012-0886-6>.
32. Singh J, Kaur K, Kumar P. Optimizing microencapsulation of alpha-tocopherol with pectin and sodium alginate. *J Food Sci Technol.* 2018;**55**(9):3625-31. [PubMed ID: 30150821]. [PubMed Central ID: PMC6098800]. <https://doi.org/10.1007/s13197-018-3288-6>.
33. Andriani D, Sunwoo C, Ryu HW, Prasetya B, Park DH. Immobilization of cellulase from newly isolated strain *Bacillus subtilis* TD6 using calcium alginate as a support material. *Bioprocess Biosyst Eng.* 2012;**35**(1-2):29-33. [PubMed ID: 21947600]. <https://doi.org/10.1007/s00449-011-0630-z>.
34. Przyklenk M, Vemmer M, Hanitzsch M, Patel A. A bioencapsulation and drying method increases shelf life and efficacy of *Metarhizium brunneum* conidia. *J Microencapsul.* 2017;**34**(5):498-512. [PubMed ID: 28699822]. <https://doi.org/10.1080/02652048.2017.1354941>.